



VicoSil™ 139DLK-CL

Order your free sample kit online

www.vicone.ca/freekit



		FDA approved Silicone 30 Duro			
Physical Property	Test Method	Unit	Result	Remark	
Tensile Strength	ASTMD412	Mpa	4,5		
Elongation at break	ASTMD412	%	570		
Permanent Set	ASTMD412	%	5,1		
Hardness	ASTMD2240	Shore A	33		
Compression Set	ASTMD395	%	20		
Density	ASTMD297	g/cc	1,19		
Heat Aging					
Change in Tensile Strength	ASTMD573	%	-17		
Change in Elongation	ASTMD573	%	-29		
Change in Hardness	ASTMD573	%	7	200°C*72h	
Effect of Liquids					
Change in Tensile Strength	ASTMD471	%	-6,8		
Change in Elongation	ASTMD471	%	-7,2		
Change in Hardness	ASTMD471	%	-7,5		
Change in Volume after Oil Immersion	ASTMD471	%	6,9		
Compression Modulus	ISO-7743	5%	10%	20%	25%
		1.6 MPa 232 PSI	1.7 MPa 247 PSI	1.8 MPa 261 PSI	1.9 MPa 276 PSI

*These specifications shall not be construed as creating an express warranty to the performance of the material. The above specifications are intended as a guideline, and may react differently under varying conditions.